



UN38.3 测试报告 UN38.3 Test Report

报告编号Report No.: S03A24070776U00601

样品名称: 可充电聚合物锂离子电池组

Sample Name: Rechargeable Li-ion polymer battery

样品型号: AEC711254 Sample Model:

委托单位: 广东国光电子有限公司

Applicant: Apower Electronics Co.,Ltd.

签发日期: 2024-09-03 Issue Date:



样品名称 Sample Name	可充电聚合物锂离子电池 组 Rechargeable Li-ion polymer battery	样品型号 Sample Model	AEC711254				
测试实验室	广东储能检测技术有限公司						
Testing laboratory	Guangdong ESTL Technology Co., Ltd.						
实验室地址 Laboratory address	广东省东莞市松山湖园区总部二路9号1栋1单元101、201-208 室、4单元201室和11号1栋2单元101室。 Room 101, 201-208, Unit 1, & Room 201, Unit 4, Building 1, No.9/Room 101, Unit 2, Building 1, No.11, Zongbu 2nd Road, Songshanhu Park, Dongguan, Guangdong, China						
委托单位	广东国光电子有限公司						
Applicant	Apower Electronics Co.,Ltd.						
委托单位地址Applicant Address	中国广东省广州市花都区新雅街镜湖大道8号 No.8, Jinghu Road of Xinya Street, Huadu District, Guangzhou City, Guangdong Province, P.R.China						
生产厂家	广东国光电子有限公司						
Manufacturer	Apower Electronics Co.,Ltd	l.					
生产厂家地址 Manufacturer Address	中国广东省广州市花都区新 No.8, Jinghu Road of Xinya Province, P.R.China		uangzhou City, Guangdong				
电芯生产单位	广东国光电子有限公司						
Factory of Cell	Apower Electronics Co.,Ltd	l.					
测试标准 Standard	联合国《试验和标准手册》第七修订版修正1第38.3节 UNITED NATIONS the "Manual of Test and Criteria" (ST/SG/AC.10/11/Rev.7+A1:2021) Section 38.3.						
接样日期 Date of sample receipt	2024-07-12						
测试日期 Tested date	2024-07-12 to 2024-07-29						

检验结论 Test conclusion:

由广东国光电子有限公司送检的可充电聚合物锂离子电池组,依据联合国《试验和标准手册》第七修订版修正**1**第38.3节进行检测,试验为全项目,测试结果符合标准相关要求。

The Rechargeable Li-ion polymer battery submitted by Apower Electronics Co.,Ltd. are tested according to UNITED NATIONS the "Manual of Test and Criteria" (ST/SG/AC.10/11/Rev.7+A1:2021) Section 38.3. The test items are full items. The test results comply with the relevant requirements of the standard.

检测 Tested by

陈保聚

审核 Reviewed by

层美娜

批准 Approved by

JA.

样品信息 Sample Information

标称电压 Nominal Voltage	3.85V	容量 Capacity	520mAh
瓦时 Watt-hour	2.002Wh	商标 Trade mark	
充电限制电压 Limited Charge Voltage	4.4V	放电终止电压 Discharge Cut-Off Voltage	3.0V
充电电流 Charge Current	260mA	最大持续充电电流 Max. Continuous Charge Current	520mA
放电电流 Discharge Current	104mA	最大持续放电电流 Max. Continuous Discharge Current	520mA
充电截止电流 End Charge Current	13mA	电池尺寸 Battery dimensions	7.55mm*12mm*57mm
电芯型号 Cell Model	711254	电芯容量 Cell Rated Capacity	520mAh
组合方式 Compound mode		1S1P	

Description of the sampling procedure: /

取样程序的说明:/

Description of the deviation from the standard, if any: /

测试结果不符合标准项的说明:/

Remarks/备注:

1. 本报告中以点代替小数点。

Throughout this report a comma is used as the decimal separator.

2. 判定栏中"-"表示"不需要判定", "P"表示"通过", "F"表示"不通过", "N/A"表示"不适用"。

As for the Verdict, "-" means "no need for judgement", "P" means "pass", "F" means "fail" and "N/A" means "not applicable".

Summary of testing:

Tests performed (name of test and test clause):

Test items	Sample Number
T.1: Altitude simulation / 高度 模拟	
T.2: Thermal test / 温度试验	
T.3: Vibration / 振动	B1 - B10
T.4: Shock / 冲击	
T.5: External short circuit / 外接短路	
T.6: Crush / 挤压 or Impact/撞 击	C1 - C10
T.7 Overcharge / 过充电	B11 - B18
T.8: Forced discharge / 强制 放电	C11 - C30

The sample's status is good.

样品状况良好。

Single cell batteries of B1~B5 B11~B14 are full charged after one cycle;

单电芯电池B1~B5 B11~B14为1次循环满电状态;

Single cell batteries of B6~B10 B15~B18 are full charged after twenty-five cycles;

单电芯电池B6~B10 B15~B18为25次循环满电状态;

Rechargeable cells of C1~C5 are 50% charged after one cycle;

可充电电芯C1~C5为1次循环后50%充电状态;

Rechargeable cells of C6~C10 are 50% charged after twenty-five cycles;

可充电电芯C6~C10为25次循环后50%充电状态;

Rechargeable cells of C11~C20 are full discharged after one cycle;

可充电电芯C11~C20为1次循环完全放电状态;

Rechargeable cells of C21~C30 are full discharged after twenty-five cycles;

可充电电芯C21~C30为25次循环完全放电状态;

Testing location:

检测地点:

广东储能检测技术有限公司

Guangdong ESTL Technology Co., Ltd.

广东省东莞市松山湖园区总部二路9号1栋1单元101、201-208室、4单元201室和11号1栋2单元101室。

Room 101, 201-208, Unit 1, & Room 201, Unit 4, Building 1, No.9/Room 101, Unit 2, Building 1, No.11, Zongbu 2nd Road, Songshanhu Park, Dongguan, Guangdong, China

Test Procedure:

1.Each battery type is subjected to tests T.1 to T.8. Tests T.1 to T.5 are conducted in sequence on the same battery. Tests 6 and 8 are conducted using not otherwise tested batteries. Test T.7 may be conducted using undamaged batteries previously used in Tests T.1 to T.5 for purposes of testing on cycled batteries.

每一种类型的电池均应进行T.1至T.8项试验。电池必须按顺序在相同的一组电池上进行试验T.1至T.5。试验T.6和T.8应使用未另外试验过的电池。试验T.7可以使用先前在试验T.1至T.5中使用过的未损坏电池进行,以便测试进行在循环过的电池上。

2.In order to quantify the mass loss, the following procedure is provided:

Mass loss(%)= $(M_1-M_2)/M_1 \times 100$

为了量化质量损失,可用以下公式计算:质量损失(%)=(M1-M2)/M1×100


Where M1 is the mass before the test and M2 is the mass after the test. When mass loss does not exceed the values in Table below, it is considered as "no mass loss".


式中: M1是试验前的质量, M2是试验后的质量。如果质量损失不超过下表所列的数值, 应视为"无质量损失"。

Mass M of cell or battery	Mass loss limit
电芯或电池的质量	质量损失限值
M<1g	0.5%
1g≤M≤75g	0.2%
M>75g	0.1%

3. In test T.1 to T.4, batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

在测试T.1至T.4中,电池须满足无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的90%。





38.3.4	Procedure / 测试步骤		判定 Verdict
38.3.4.1	Test 1: Altitude simulation / 测试1: 高度模拟		Р
	Test cells and batteries shall be stored at a pressure of 11.6kPa or less for at least six hour at ambient temperature (20±5℃). 试验电芯和电池在温度为20±5℃,大气压力为不大于11.6kpa 的环境中贮存不少于6 个小时。		Р
	Requirement / 标准要求: 1. Cells and batteries Mass loss limit: ≤0.2%. 样品质量损失≤0.2%。 2. Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的90%,此要求不适用于完全放完电的电芯和电池。 3. No leakage, no venting, no disassembly, no rupture and no fire. 样品应无漏液、无排气、无解体、无破裂以及无着火现象的发生。	No leakage, no venting, no disassembly, no rupture and no fire. 无漏液、无排气、无解体、无破裂以及无着火现象。 The data see table 1. /测试数据见表1。	Р
38.3.4.2	Test 2: Thermal test / 测试 2: 温度试验		P
	Test cells and batteries are to be stored for 试验电芯和电池存储条件如下: 1. one temperature cycle: 72±2℃(6h) — -40±2℃(6h). —次温度循环为72±2℃(6h) — -40±2℃(6h)。 2. The maximum time interval between test temperature extremes is 30 minutes. 温度转换最大间隔时间为30mins。 3. This procedure is to be repeated 10 times. 重复10 次循环。 4. after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20±5℃). 循环结束后,所有试验电芯和电池在 20±5℃的条件下 搁置24 小时。		P
	Requirements / 标准要求: 1. Cells and batteries Mass loss limit: ≤0.2%. 样品质量损失≤0.2%。 2. Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的90%,此要求不适用于完全放完电的电芯和电池。 3. No leakage, no venting, no disassembly, no rupture and no fire. 样品应无漏液、无排气、无解体、无破裂以及无着火现象的发生。	No leakage, no venting, no disassembly, no rupture and no fire. 无漏液、无排气、无解体、无破裂以及无着火现象。 The data see table 1. /测试数据见表1。	P
38.3.4.3	Test 3: Vibration / 测试 3: 振动		Р
	Cells and batteries are firmly secured to the platform of		Р

	the vibration machine.		
	电芯和电池牢固地安装在振动台(的台面)上。		
	2. The vibration :a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes.		
	振动以正弦波形式,以7Hz 增加至200Hz,然后在减少回到7Hz 为一个循环,一个循环持续15 分钟的对数前移传送。		
	3. the logarithmic frequency sweep is as follows: from 7 Hz a peak acceleration of 1 gn is maintained until 18 Hz is reached, The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 gn occurs (approximately 50Hz), A peak acceleration of 8 gn is then maintained until the frequency is increased to 200 Hz.		
	对数扫频为:从7 赫兹开始保持1gn 的最大加速度直到频率为18 赫兹,然后将振幅保持在0.8 毫米(总偏移1.6 毫米)并增加频率直到最大加速度达到8gn(频率约为50 赫兹),将最大加速度保持在8gn 直到频率增加到200 赫兹。		
	4. This cycle repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting position of the cell. One of the directions of vibration must be perpendicular to the terminal face.		
	以振动的其中一个方向必须是垂直样品极性,对每个电芯 从三个互相垂直的方向上循环12次,每个方向3个小时, 共9小时。		
	Requirements / 标准要求:	No leakage, no venting,	Р
	1. Cells and batteries Mass loss limit: ≤0.2%.	no disassembly, no rupture and no fire.	
	样品质量损失≤0.2%.	无漏液、无排气、无解	
	2. Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states.	体、无破裂以及无着火 现象。	
	样品试验后开路电压应不低于试验前开路电压的90%,此要求不适用于完全放完电的电芯和电池。	The data see table 1. /测试数据见表1。	
	3. No leakage, no venting, no disassembly, no rupture and no fire.		
	样品应无漏液、无排气、无解体、无破裂以及无着火现象 的发生。		
38.3.4.4	Test 4: Shock / 测试 4: 冲击		Р
	Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery. Each cell or battery shall be subjected to a half-sine shock of peak acceleration of 150 gn and pulse duration of 6 milliseconds. Alternatively, large cells may be subjected to a half-sine shock of peak acceleration of 50 gn and pulse duration of 11 milliseconds.		P
	试验电芯和电池应通过坚固的方式紧固在试验设备上,可以支撑每个被测电池的所有面。每个电芯或电池应用峰值加速度150 gn、脉冲时间6 ms的半正弦波进行冲击。或者大电芯应用峰值加速度50 gn、脉冲时间11 ms的半正弦波进行冲击。		

	peak acceled The pulse of batteries are formulas be minimum p 每个电池应的质量。小	ry shall be subjected to a hall eration depending on the maduration shall be 6 millisecond 11 milliseconds for large below are provided to calculate eak accelerations. 用半正弦波冲击的峰值加速度电池应用6 ms的脉冲时间以过间。根据下面的公式来计算	ttery. e oriate 一电池 用11		Р	
	Battery	Minimum peak acceleration	Pulse duration			
	Small	150 gn or result of formula Acceleration (gn)				
	batteries	$= \sqrt{\left(\frac{100850}{mass*}\right)}$ Whichever is smaller	6ms			
	Large batteries	50 gn or result of formula Acceleration (gn) $= \sqrt{\left(\frac{30000}{mass *}\right)}$	11ms			
		Whichever is smaller				
	positive direction in mounting p shocks.	r battery is subjected to three ection and to three shocks in each of three mutually perpositions of the cell or battery 电池应在三个垂直面的正向符受3次冲击,共18次。	e f 18		Р	
	1. Cells and 样品质量损 2. Open cir requiremen	cuit voltage not less than 90 it relating to voltage is not ap	%, The oplicable to t	est	No leakage, no venting, no disassembly, no rupture and no fire. 无漏液、无排气、无解体、无破裂以及无着火现象。	Р
	样品试验后	atteries at full discharged sta 开路电压应不低于试验前开路 完全放完电的电芯和电池。		6,此要	The data see table 1. /测试数据见表1。	
	and no fire.	ige, no venting, no disassem 液、无排气、无解体、无破系				
38.3.4.5	Test 5: Ext	ternal Short Circuit / 测试5	外接短路			Р
	stabilized s 57±4℃.	or battery to be tested shall l o that its external case temp	erature read	ches		Р
	保持试验环 表温度达到	境温度稳定在 57±4℃ ,以使 57±4℃ 。	电芯或电池构	羊品外		
		or battery shall be subjected vith a total external resistance				

	ohm at 57±4℃, This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 57±4℃.		
	将样品正负极用小于0.1Ω的总电阻回路进行短路,样品的外表温度恢复到57±4℃之后保持短路状态1小时以上。		
	3. the cell or battery must be observed for a further six hour for the test to be concluded.		
	对电芯或电池必须进一步观察6个小时才能下结论。		
	Requirements / 标准要求:	External temperature	Р
	During the test and within six hours after test, the cells or batteries.	not exceed 170℃ 外表温度不超过170℃	
	在测试过程中以及之后6个小时内,电芯或电池样品。	No disassembly, no	
	1. External temperature not exceed 170 $^{\circ}\!$	rupture and no fire.	
	外表温度不超过170℃。	无解体、无破裂和无着 业现免发生	
	2. No disassembly, no rupture and no fire.	火现象发生。 The data see table 1.	
	样品应无解体、无破裂和无着火现象发生。	/测试数据见表1。	
22.2.4.2	- And Andrews	/ 例 风 致 1 / 2 / 2 / 3 / 5	
38.3.4.6	Test 6: Impact / Crush / 测试6: 撞击 / 挤压		Р
	Impact (applicable to cylindrical cells not less than 18mm in diameter).		N/A
	撞击(适用于直径不小于18 毫米的圆柱形电芯)。		
	1. This test sample cell or component cell is to be placed on a flat smooth surface.		N/A
	将试验样品用的电芯或元件电芯放在一个平坦光滑的平面 上。		
	2. A 15.8mm±0.1mm diameter bar is to be placed across the center of the sample, A 9.1kg±0.1kg mass is to be dropped from a height of 61±2.5cm onto the sample.		
	将一直径为15.8mm±0.1mm的钢棒横过电池中部放置后,将一质量为9.1kg±0.1kg的物体从61±2.5cm的高度落向样品。		
	3. The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8mm±0.1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact.		
	接受撞击的试样,纵轴应与平坦的表面平行并与横放在试样中心的直径15.8mm±0.1mm弯曲表面的纵轴垂直。每一个试样只经受一次撞击。		
	Requirements / 标准要求:		N/A
	1. Test cells or component cells external temperature not exceed 170 $^{\circ}\mathrm{C}$.		
	电芯或元件电芯的最高表面温度应不超过170℃。		
	2. No disassembly and no fire within six hours of this test.		
	试验结束后6个小时之内,应无解体和无着火现象发生。		
	Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18mm in diameter).		Р
	挤压(适用于棱柱形、袋装、硬币/纽扣电芯和直径小于 18 毫米的圆柱形电芯)。		
	A cell or component cell is to be crushed between two	The applied force	Р
	1	1 ''	

flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached. 将电芯或元件电芯放在两个平面之间挤压、挤压力度逐渐加大,在第一个接触点上的速度为31.5 厘米秒。挤压 持续进行,直到比别以下一种情况之一。 (a) The applied force reaches 13 kN ± 0.78 kN. 施加的力达到13 千牛±0.78 千牛。(b) The voltage of the cell drops by at least 100 mV. 电芯的电压下降至少100 毫伏。(c) The cell is deformed by 50% or more of its original thickness. 电芯变形证图新厚度的50%以上。 2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. 技柱形或皮色区或从元度的一面旋压、组扎原币形电池 应从其平坦表面施压。圆柱形电芯成从与线性型内心、2. No disassembly no rupture and no fire within six hours of this test 试验结束后个小时之内,电芯和聚合物电芯应定解体、无碳型和无管大观象发生。 ***********************************				
#中述或元件中志放在两个下面之间报乐,挤压力度连新加大、在第一个接触上台的地理大约1.5 厘米/砂。挤压持续进行,直到由现以下三种情况之一: (a) The applied force reaches 13 kN ± 0.78 kN. 施加的力达到13 千半±0.78 千半。 (b) The voltage of the cell drops by at least 100 mV. 电心的电压下降至少100 毫伏。 (c) The cell is deformed by 50% or more of its original thickness. 电芯变形达原始序度的50%以上。 2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. 校柱形或袋装电芯应从最宽的一面能压。组扣级币形电池应从其平担表面施压。固柱形电芯应从与纵轴垂直的方向施压。 Requirements / 标准要求: 1. Cells external temperature not exceed 170°C. 电芯或电池的最高表面温度应不超过170°C。 2. No disassembly no rupture and no fire within six hours of this test 试验结束后6个小时之内,电芯和聚合物电芯应无解体、无破裂和无者火现象发生。 无破裂和无者火现象发生。 The data see table 2. / 阅读数据见表2. 38.3.4.7 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制旋厂惟存的最大持续充电电压对并最充电。 2. The minimum voltage of the test shall be the lesser of two times the maximum charge voltage is nor than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 12 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 12 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 12 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 12 times the maximum charge voltage. 如果厂家推荐的充土电压闭过18V, 本测试的最小充电电压可是厂家标准的充土电压可是工家标准的充土电压可是工家标准的充土电压可是工家标准的表示。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 12 times the maximum charge voltage. 如果厂家推荐的充土电压闭过18V, 本测试的最小充电电压可能式 to the conducted at ambient temperature		of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three	kN. 施加的力达到13 千牛	
i 施加的力达到13 千年±0.78 千年。 (b) The voltage of the cell drops by at least 100 mV. 电芯的电压下降至少100 总伏。 (c) The cell is deformed by 50% or more of its original thickness. 电芯变形达原始序度的50%以上。 2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. 校社形或袋卖也志应从最宽的一面施压。饲料形电池应从其中地池应从其中进表面施压。饲料形电池应从其中地表面施压。饲料形电池应从与纵轴垂直的方向施压。 Requirements / 标准要求: 1. Cells external temperature not exceed 170°C. 电心或电池的最高表面温度应不超过170°C。 2. No disassembly no rupture and no fire within six hours of this test 试验结束后6个小时之内,电心和聚合物电心应光解体、无破裂和无着大现象发生。 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 何制造广推整的最大转旋充电电、2. The minimum voltage of the test shall be 12 (有制定广推整的最大转旋和电压和对射性显示。 a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. Tests are to be conducted at ambient temperature		加大,在第一个接触点上的速度大约为1.5 厘米/秒。挤压		
(b) The voltage of the cell drops by at least 100 mV. 电芯的电压下降至少100 毫伏。 (c) The cell is deformed by 50% or more of its original thickness. 电心变形达限始厚度的50%以上。 2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. 校杜形或爱黎电心成从最宽的一面施压。组扣/顺币形电池应从其平坦表面施压。圆柱形电心应从其平坦表面施压。圆柱形电心应从与纵轴垂直的方向施压。 Requirements / 标准要求: 1. Cells external temperature not exceed 170°C. 电芯或电池的最高表面温度应不超过170°C。 2. No disassembly no rupture and no fire within six hours of this test 试验结束后个小时之内,电芯和聚合物电芯应无解体、无破裂和无者火现象发生。 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以 2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be the lesser of two times the maximum charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压超过18V,本测试的最小充电电压成光 / 测试电压分 8, 8V,电流为1.04A. P P The voltage of the test shall be as follows: 本测试量小电压不超过18V,本测试的最小充电电压分 1.04A. 测试电压为 8, 8V,电流为1.04A. B N 中压及 1.04A. P P D N hen the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18		(a) The applied force reaches 13 kN \pm 0.78 kN.		
电芯的电压下降至少100 毫伏。 (c) The cell is deformed by 50% or more of its original thickness. 电心变形这原始厚皮的50%以上。 2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A buton/coin cell shall be crushed by applying the force to the videst side. A buton/coin cell shall be crushed by applying the force to the side shall be applied perpendicular to the longitudinal axis. ***** *****************************		施加的力达到13 千牛±0.78 千牛。		
(c) The cell is deformed by 50% or more of its original thickness. 电心变形达原始厚度的50%以上。 2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force to flow widest side. A button/coin cell shall be crushed by applying the force to flow its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis.		(b) The voltage of the cell drops by at least 100 mV.		
thickness. 电志变形达原始厚度的50%以上。 2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. 楼柱形或袋装电芯应从最宽的一面遮压。纽柱形电芯应从与级轴垂直的方向施压。 Requirements / 标准要求: 1. Cells external temperature not exceed 170°C. 电芯或电池的最高表面温度应不超过170°C。 2. No disassembly no rupture and no fire within six hours of this test it 试验结束后6 个小时之内,电芯和聚合物电芯应无解体、无破裂和无着火现象发生。 The data see table 2. 测试数据见表2。 38.3.4.7 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be as follows: 未测试最小电压为: a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压和过18V, 未测试的最小充电电压处是)"家标定最大允电电压的两倍或者是22V之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended c		电芯的电压下降至少100毫伏。		
2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surface. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. 核柱形或袋装电芯应从最宽的一面施压。组扣/便币形电池应从其"坦表面施压。圆柱形电芯应从与纵轴垂直的方向施压。 Requirements / 标准要求: 1. Cells external temperature not exceed 170°C. 电芯或电池的最高表面温度应不超过170°C。 2. No disassembly no rupture and no fire within six hours of this test 试验结束后6个小时之内,电芯和聚合物电芯应无解体、无破裂和无着火现象发生。 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be the lesser of two times the maximum charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压和过18V, 本测试的最小充电电压的2.6 份。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. b) When the maximum charge voltage. c) Start and temperature the test shall be 1.2 times the maximum charge voltage. d) Start and temperature the test shall be 1.2 times the maximum charge voltage. d) Start and temperature the test shall be 1.2 times the maximum charge voltage. d) Start and temperature the test shall be 1.2 times the maximum charge voltage. d) Start and temperature the test shall be the test shall be 1.2 times the maximum charge voltage. d) Start and temperat		1, ,		
the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. 核柱形或袋髮电芯应从最宽的一面施压。组打/硬币形电池应从其平坦表面施压。圆柱形电芯应从与纵轴垂直的方向施压。 Requirements / 标准要求: 1. Cells external temperature not exceed 170℃. 电芯或电池的最高表面温度应不超过170℃。 2. No disaassembly no rupture and no fire within six hours of this test 试验结束后6个小时之内,电芯和聚合物电芯应无解体、无破裂和无着火现象发生。 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be the lesser of two times the maximum charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage, multiple is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage, multiple is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage, multiple is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage, multiple is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage, multiple is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage, multiple is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage, multiple is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage, multiple is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 3. Tests are to be conducted at ambient temperature		电芯变形达原始厚度的50%以上。		
perpendicular to the longitudinal axis. 核柱形或袋装电芯应从最宽的一面施压。组扣硬币形电池应从其平坦表面施压。圆柱形电芯应从与纵轴垂直的方向施压。 Requirements / 标准要求: 1. Cells external temperature not exceed 170℃. 电芯或电池的最高表面温度应不超过170℃。 2. No disassembly no rupture and no fire within six hours of this test 试验结束后6个小时之内,电芯和聚合物电芯应无解体、无破裂和无着火现象发生。 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be the lesser of two times the maximum charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V, 本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature		the force to the widest side. A button/coin cell shall be		
应从其平坦表面施压。圆桂形电芯应从与纵轴垂直的方向施压。 Requirements / 标准要求: 1. Cells external temperature not exceed 170℃. 电芯或电池的最高表面温度应不超过170℃。 2. No disassembly no rupture and no fire within six hours of this test 试验结束后6个小时之内,电芯和聚合物电芯应无解体、无破裂和无着火现象发生。 The data see table 2. / 测试数据见表2。 38.3.4.7 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be the lesser of two times the maximum charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压不超过18V, 本测试的最小充电电压应是厂家标定最大充电电压的两倍或者是22V之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) The voltage of the test is 8.8V, and the current is 1.04A. / 测试电压为 8.8V, 电流为1.04A. D) The voltage of the test is 8.8V, 电流为1.04A. D) When the manufacturer's recommended charge voltage of the battery or 22V. D) The minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) The more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) The more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) The control to the control to the voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. D) The control to the test shall be 1.2 times the maximum charge voltage.		perpendicular to the longitudinal axis.		
1. Cells external temperature not exceed 170℃. 电式或电池的最高表面温度应不超过170℃。 2. No disassembly no rupture and no fire within six hours of this test		应从其平坦表面施压。圆柱形电芯应从与纵轴垂直的方向		
用さび東上部 temperature not exceed 170℃。 电芯或电池的最高表面温度应不超过170℃。 2. No disassembly no rupture and no fire within six hours of this test 试验结束后6 个小时之内,电芯和聚合物电芯应无解体、无解体、无破裂和无着火现象发生。 The data see table 2. /测试数据见表2。 38.3.4.7 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be as follows: 本测试最小电压为: a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压不超过18V,本测试的最小充电电压应是厂家标定最大充电电压的两倍或者是22V 之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V,本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature		Requirements / 标准要求:		P
2. No disassembly no rupture and no fire within six hours of this test		1. Cells external temperature not exceed 170℃.	not exceed 170°C	
2. No disasseribly no rupture and no fire within six hours of this test 试验结束后6 个小时之内,电芯和聚合物电芯应无解体、无破裂和无着火现象发生。 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以 2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be as follows: 本测试最小电压为: a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压不超过18V,本测试的最小充电电压应是厂家标定最大充电电压的两倍或者是22V 之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V,本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature		电芯或电池的最高表面温度应不超过170℃。	外表温度不超过170℃	
大破裂和无着火现象发生。 Test 7: Overcharge / 測试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be as follows: 本測试最小电压为: a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压不超过18V, 本测试的最小充电电压成是厂家标定最大充电电压的两倍或者是22V 之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V, 本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature				
The data see table 2. /测试数据见表2。 Test 7: Overcharge / 测试 7: 过充电 1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be as follows: 本测试最小电压为: a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压不超过18V,本测试的最小充电电压应是厂家标定最大充电电压的两倍或者是22V 之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V,本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature			1	
1. The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be as follows: 本测试最小电压为: a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压不超过18V,本测试的最小充电电压应是厂家标定最大充电电压的两倍或者是22V 之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V,本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature				
recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be as follows: 本测试最小电压为: a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压不超过18V,本测试的最小充电电压应是厂家标定最大充电电压的两倍或者是22V 之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V,本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature	38.3.4.7	Test 7: Overcharge / 测试 7: 过充电		Р
voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 如果厂家推荐的充电电压不超过18V,本测试的最小充电电压应是厂家标定最大充电电压的两倍或者是22V 之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V,本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature		recommended maximum continuous charge current. 以2 倍制造厂推荐的最大持续充电电流对样品充电。 2. The minimum voltage of the test shall be as follows:	is 8.8V, and the current is 1.04A. / 测试电压为	Р
电压应是厂家标定最大充电电压的两倍或者是22V 之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V,本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature		voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge		
voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 如果厂家推荐的充电电压超过18V,本测试的最小充电电压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature		电压应是厂家标定最大充电电压的两倍或者是22V 之中的		
压应是厂家标定最大充电电压的1.2 倍。 3. Tests are to be conducted at ambient temperature		voltage is more than 18V, the minimum voltage of the test		
· · · · · · · · · · · · · · · · · · ·				
		·		

	20±5℃的环境温度下,试验持续24 小时。		
	Requirements / 标准要求: No disassembly and no fire within seven days of this test. 试验样品在试验中和试验后7 天内,应无解体和无着火现象发生。	No disassembly and no fire 无解体和无着火现象发生。 The data see table 2. /测试数据见表2。	Р
38.3.4.8	Test 8: Forced discharge / 测试 8: 强制放电		Р
	Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12 V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer. 20±5℃的环境温度下,将单个电芯连接在12V的直流电源上进行强制放电,此直流电源提供给每个电芯初始电流为		Р
	制造厂指定的最大放电电流。		
	The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere). 指定的放电电流通过串联在测试电芯上的合适大小和功率的负载来获得,每个电芯的强制放电时间(小时)为额定容量除以初始电流(安培)。		Р
	Requirements / 标准要求:	No disassembly and no	Р
	No disassembly and no fire within seven days of this test. 试验样品在试验中和试验后7 天内,应无解体和无着火现象发生。	fire. 无解体和无着火现象。 The data see table 2. /测试数据见表2。	

	Table 1: T1-T5 / 表1. 试验1-试验5										
Sample No. / 样品 编号	Mass prior to test / 试验前 质量(g)	OCV prior to test / 试验前 电压(V)	simu	Altitude lation 高度模拟		nermal test 温度实验		Vibration 3: 振动		: Shock 4: 冲击	Test 5: External Short Circuit 测试 5: 外接短路
			Mass loss(%) 质量损失 (%)	Change ratio 电压比(%)	Mass loss(%) 质量损失 (%)	Change ratio 电压比(%)	Mass loss(%) 质量损失 (%)	Change ratio 电压比(%)	Mass loss(%) 质量损失(%)	Change ratio 电压比(%)	Temp. (℃) 温度 (℃)
B1	8.055	4.383	0.000	99.98	0.050	98.93	0.000	100.00	0.000	100.00	57.8
B2	8.129	4.385	0.012	99.95	0.037	98.93	0.000	100.00	0.012	100.00	57.9
В3	8.138	4.384	0.000	99.98	0.037	98.86	0.012	100.00	0.000	100.00	57.8
B4	8.132	4.383	0.000	99.98	0.049	98.90	0.000	99.98	0.000	100.00	57.7
B5	8.202	4.384	0.012	99.98	0.061	98.90	0.000	100.00	0.000	99.98	56.8
В6	8.105	4.383	0.000	99.95	0.037	98.90	0.012	100.00	0.000	100.00	57.0
В7	8.126	4.383	0.000	99.98	0.037	98.86	0.000	99.98	0.000	100.00	57.2
В8	8.163	4.385	0.012	99.95	0.049	98.93	0.000	100.00	0.000	100.00	57.4
В9	8.121	4.383	0.000	99.98	0.037	98.90	0.012	99.98	0.000	100.00	58.4
B10	8.095	4.383	0.012	99.98	0.049	98.93	0.000	100.00	0.000	100.00	57.0

Table 2: T6-T8 / 表2. 试验6-试验8							
	it 6: Impact / (测试6: 撞击 /拐			vercharge ':过充电	Test 8: Forced discharge / 测试8: 强制放电		
Sample No. / 样品 编号	OCV prior to test / 试 验前电压 (V)	Temp. (℃) / 温度 (℃)	Sample No. / 样品编号	OCV prior to test / 试验前电 压(V)	Sample No. / 样 品编号	OCV prior to test / 试验前电压(V)	
C1	3.823	23.5	B11	4.384	C11	3.355	
C2	3.825	23.1	B12	4.385	C12	3.351	
C3	3.821	23.9	B13	4.382	C13	3.353	
C4	3.826	22.9	B14	4.383	C14	3.356	
C5	3.819	22.6	B15	4.383	C15	3.359	
C6	3.825	23.3	B16	4.385	C16	3.358	
C7	3.829	23.4	B17	4.382	C17	3.355	
C8	3.824	22.5	B18	4.384	C18	3.351	
C9	3.827	22.7			C19	3.352	
C10	3.822	22.9			C20	3.354	
					C21	3.357	
					C22	3.356	
					C23	3.355	
					C24	3.352	
					C25	3.351	
					C26	3.355	
					C27	3.359	
					C28	3.356	
					C29	3.353	
					C30	3.351	

--- 报告结束 ---

--- End of Report ---

声明

Declaration

1. 本报告无批准人、审核人及检测人签名无效。

The test report is invalid without the signatures of Ratifier, Reviewer and Testing engineer.

2. 对检验报告若有异议,应于收到报告之日起十五天内向检验单位提出。

Objections to the test report must be submitted to ESTL within 15 days.

3. 未经本试验室书面同意,不得部分地复制本报告。

Nobody is allowed to photocopy or partly photocopy this test report without written permission of ESTL.

4. 客户必须如实提供样品及资料,并保证申报品名和样品以及运输货物相同,否则本检测单位不承担任何相关责任。

The client should provide samples and relevant data, at the same time, they should guarantee the consistence of the product's name the declared, the samples they provided and the goods to be transported. Otherwise we will not bear any relevant responsibilities.

5. 本报告仅对送检样品负责。

The test report is valid for the tested samples only.

6. 任何情况下检测单位的赔偿责任都不会超过检测单位就本次检测所收取的检测费用。

ESTL's liability under no circumstance will exceed the testing fee received from applicant for test conducted hereof this testing report.

7. 本报告涂改无效。

The test report is invalid if altered.

8. 本报告无本公司"检测报告专用章"或"公章"无效。

This report is invalid without the company's "Special seal for Test Report" or "official seal".

9. 本报告未加盖CMA资质认定标志,不具有社会证明作用,本公司不承担因此引发的任何风险和法律责任。

This report is not stamped with CMA qualification certification mark, which does not have the function of social proof, and the Company does not assume any risks and legal liabilities caused by this.